National Institute of Advanced Industrial Science and Technology

National Metrology Institute of Japan



Reference Material Certificate

NMIJ CRM 5807-a No. +++



Al₂O₃-TiC Ceramics for Thermal Diffusivity Measurement

This certified reference material (CRM) is produced in accordance with the NMIJ's management system and is in compliance with ISO 17034 and ISO/IEC 17025. This CRM is intended for use in the calibration and validation of instruments for thermal diffusivity measurements for example, the flash method.

Certified Values

The certified value for thermal diffusivity α and the relative expanded uncertainties U of this CRM are given from the following equations. The uncertainty U is the half-width of the relative expanded uncertainty interval calculated using a coverage factor (k) of 2, and it is the half-width of an interval estimated to have a level of confidence of approximately 95 %.

$$\alpha/(m^{2}s^{-1}) = 7.505 \times 10^{-7} + 9.589 \times 10^{-7} \cdot exp\left(\frac{6.635 \times 10^{2}}{(T/K)}\right)$$
(300 K $\leq T \leq 1000$ K)

$$U = 6.1 \% (300 \text{ K} \leq T < 380 \text{ K})$$

$$U = 5.1 \% (380 \text{ K} \leq T < 593 \text{ K})$$

$$U = 6.1 \% (593 \text{ K} \leq T < 758 \text{ K})$$

$$U = 7.1 \% (758 \text{ K} \leq T < 921 \text{ K})$$

$$U = 8.1 \% (921 \text{ K} \leq T \leq 1000 \text{ K})$$

The calculated results from the above equations at typical temperature points of this CRM are shown in the table below.

Temperature <i>T</i> (K)	Certified value α (m ² ·s ⁻¹)	Relative expanded uncertainty <i>U</i> (%)
300	9.51×10⁻ ⁶	6.1
400	5.79×10⁻ ⁶	5.1
500	4.37×10 ^{−6}	5.1
600	3.65×10 ^{−6}	6.1
700	3.22×10 ^{−6}	6.1
800	2.95×10 ^{−6}	7.1
900	2.75×10 ^{−6}	7.1
1000	2.61×10 ^{−6}	8.1

Analysis

The certified values (thermal diffusivity) were determined using the laser flash method.

99 specimen-sets of the reference material were prepared from one plate of Al_2O_3 -TiC ceramics (100 mm × 100 mm × 10 mm). The specimen-sets consisted of three disk-shaped specimens 10 mm in diameter and 1, 2, and 3 mm in thickness, respectively. Nine specimens (two 1-mm-thick disks, five 2-mm-thick disks, and two 3-mm-thick disks) were sampled for determination of the thermal diffusivity of this CRM. Thermal diffusivities at 300 K, 500 K, 640 K, 760 K, 880 K and 1000 K of the 9 specimens were measured in vacuum. The thermal diffusivity as a function of temperature of this CRM was determined by the least-squares

Date of Shipment: Xxxxx XX, 20XX

fitting to all measured thermal diffusivities of the 9 specimens.

Metrological Traceability

Thermal diffusivity derived from specimen thickness and heat diffusion time was determined by the primary measurement system for thermal diffusivity at NMIJ, which was calibrated by using block gauges, a function generator, and an R-type thermocouple, which were calibrated to be traceable to the International System of Units (SI). The certified values (thermal diffusivity), therefore, are traceable to the SI.

Expiration of Certification

This certificate is valid from the date of shipment to March 31, 2030, provided that this CRM is stored in accordance with the instructions given in this certificate.

Description of the Material

This CRM consists of three black disks with diameters of 10 mm and respective thicknesses of 1 mm, 2 mm and 3 mm. The three disks are kept in a plastic container.

Instructions for Storage

This CRM should be stored at a temperature of 23 °C \pm 10 °C and a relative humidity of 50 % or less

Instructions for Use

- · This CRM is to be used only for testing and experimental studies.
- This CRM can be measured without the black coating for the flash method. Measure the thickness of each specimen with a 1 µm resolution at room temperature before use, and calculate the thermal diffusivity using the thickness.
- · Use this CRM in vacuum or inert gas flow (Ar, etc.) above room temperature.
- · It is not available for use when this CRM is given some damages, for example, cracks and strain.
- It is not available for use when some substances is absorbed or attached in the CRM because of change of thermal diffusivity.

Precautions for Handling

Handling of this CRM is similar to that of solid-state ceramics. Refer to the safety data sheet (SDS) on this CRM before use.

Preparation

These CRM specimens were prepared from one plate (100 mm \times 100 mm \times 10 mm) of NPA-2 produced by Nippon Tungsten CO., Ltd. NPA-2 is a grade of Al₂O₃-TiC ceramics.

Technical Information

No significant variation in thermal diffusivity of a specimen of this CRM was detected after five cycles of heating and cooling process in which temperatures were varied between 300 K and 1000 K in vacuum or inert gas flow. Reactivity to typical heat-resistant materials: There was no reaction with α -Alumina (Al₂O₃) and boron nitride (BN) in the temperature range from room temperature to 1000 K and in vacuum or inert gas flow.

NMIJ Analysts

The technical manager for this CRM is YAMADA N., the production manager and analyst are AKOSHIMA M.

Information

If substantive technical changes occur that affect the certification before the expiration of this certificate, NMIJ will notify the registered customer. Customer registration on the NMIJ Website (given below) will facilitate notification. Technical reports regarding this CRM can be obtained from the contact details given below.

Reproduction of Certificate

In reproducing this certificate, it should be clearly indicated that the document is a copy.

April 1, 2020

ISHIMURA Kazuhiko President National Institute of Advanced Industrial Science and Technology

If you have any questions about this CRM, please contact: National Institute of Advanced Industrial Science and Technology, National Metrology Institute of Japan, Center for Quality Management of Metrology, Reference Materials Office, 1-1-1 Umezono, Tsukuba, Ibaraki 305-8563, Japan Phone: +81-29-861-4059; https://unit.aist.go.jp/nmij/english/refmate/

Revision history

April 1, 2015:"Metrology Management Center" was renamed to "Center for Quality Management of Metrology."February 20, 2019:The limit of validity of the report was extended from "March 31, 2020" to "March 31, 2025."May 30, 2025:The limit of validity of the report was extended from "March 31, 2025" to "March 31, 2030."

